

Test Report

Report Number:
261475-7-NDT



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 4
Init.: JNAS/JHA
Order no.: 261475
Encl.: 2

Assignor: AJ PRODUKTER AKTIEBOLAG, Transportvägem 23, 301 82 Halmstad, Sweden

Item: **Table Verticus/Alva** - The test also covers **Table Verticus/Alva** height 500 and 720 mm. See enclosure B for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 9 December 2024.

Period: The test took place from 10 December 2024 to 20 March 2025.

Method: EN 15372:2023 - Furniture – Strength, durability and safety – Requirements for non-domestic tables
Test severity L2: General use: E.g. in general hotel, libraries, cafés, restaurants, public halls, banks, bars, meeting rooms, canteens, break-out areas.
Additional test methods that are referred to are listed in enclosure B.

Test results: **Passed.**
The detailed results are shown in enclosure A.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Building and Construction

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.
Jacob Næsby
Consultant



DANAK
TEST Reg.no. 2



Results

Test No.	Test	Test Method	Loading		Result
5.1	General requirements				Passed
5.2	Holes in tubular/rigid component				N/A
5.3.2	Shear and compression points when setting up and folding				N/A
5.3.3	Shear and compression points under influence of non-electrically powered mechanisms				N/A
5.3.4	Shear and compression points during use				Passed
5.4.1.2	Stability under vertical load test - height \leq 950 mm	EN 1730, 7.2.2	Main surface Ancillary surface	200 100	Passed
5.4.1.3	Stability under vertical load test - height > 950 mm	EN 1730, 7.2.3	Main surface Ancillary surface		N/A
5.4.2	Stability for tables with extension elements	EN 1730, 7.3	Test force, N	200	N/A
5.5.1-1	Durability of height adjustment mechanisms	EN 1730, 8	Specified mass, kg Cycles	50 5000	N/A
5.5.1-2	Horizontal static load test	EN 1730, 6.2	Test force, N Specified mass, kg Cycles	241 50 10	Passed
Comment	The loading was reduced from 300N to 241N to avoid overturning				
5.5.1-3	Vertical static load on main surface	EN 1730, 6.3.1	Test force, N Cycles	1250 10	Passed
5.5.1-4	Additional vertical static load test where the main surface has a length >1600 mm	EN 1730, 6.3.2	Test force, N Cycles	1000 10	N/A
5.5.1-5	Vertical static load on ancillary surface	EN 1730, 6.3.3	Test force, N Cycles	300 10	N/A
5.5.1-6	Horizontal durability test	EN 1730, 6.4.1 and 6.4.2	Test force, N Specified mass, kg Cycles	300 50 15	Passed
5.5.1-7	Vertical durability test for cantilever and tables with central column only	EN 1730, 6.5	Test force, N Cycles	300 15000	Passed
5.5.1-8	Vertical impact test for glass tabletops	EN 1730, 6.6.1 and 6.6.2	Drop height, mm Cycles	240 10	N/A
5.5.1-9	Vertical impact test for all other tabletops	EN 1730, 6.6.1 and 6.6.3	Drop height, mm Cycles	180 10	Passed
5.5.1-10	Drop test – This test is applicable for tables weighing more than 20 kg only	EN 1730, 6.9	Drop height, mm Cycles	 6	N/A
6	Information for use				Passed
B.1.2.3	Deflection of table tops	EN 1730, 6.7	Distributed load, Kg	54	Passed
B.1.3.2	Durability of table with castors	EN 1730, 6.8	Specified load, Kg Cycles	20 2000	N/A



Methods

The following standard methods are used in this test report:

EN 15372:2023 - Furniture – Strength, durability and safety – Requirements for non-domestic tables

EN 1730:2012 - Furniture - Tables - Test methods for the determination of stability, strenght and durability

Measurement uncertainty: Decision rule according to EN ISO IEC 17025:2018 clause 3.7: No account is taken of measurement uncertainty when reporting numerical results.

Sample

Description of the item tested:

Model:	Table Verticus/Alva
Type:	Tabe
Width:	700 mm
Length:	700 mm
Height:	900 mm
Weight:	18.08 kg
Materials:	Metal / laminated particleboard



Photo of the sample as received:

